

Abstract of the Disclosure

A photoconductor having a charge generation layer and a charge transport layer, the charge transport layer having hydrazone or aryl amine charge transport molecules and also having as room light protective additives acetosol yellow 5GLS and tetraphenylcyclopentadienone or 9-fluorenone. Preferably the amount of the acetosol yellow is 2 to 4 percent by weight of the weight of the charge transfer layer and the ratio of weight between the acetosol yellow and the dienone or fluorenone is in the range of 1:1 to 1:3.